



EVERLAST FLOOR

HEALTHY DURABLE ATTRACTIVE

EVERLAST FLOOR™

EE101

DESCRIPTION

EVERLAST FLOOR® is a 100% solids epoxy, marble-chip and quartz aggregate that is troweled in place, evenly textured, slip-resistant finish with a thickness of between 1/8" and 3/16". EVERLAST FLOOR® does not require primer or bond coat components or the application thereof. EVERLAST FLOOR® can withstand subtle movement of the sub-floor and is not prone to cracking. EVERLAST FLOOR® meets all of the USDA guidelines for use in federally inspected facilities.

EVERLAST FLOOR® is a monolithic, custom-made, troweled on system that forms a physical bond between the material and the surface it is being applied and vulcanizes them together. The compound made is so tightly bonded together that corrosive materials cannot penetrate to begin the process of deterioration.

RECOMMENDED USES

EVERLAST FLOOR® lends itself to many types of the industry's needs. **Retail** it's a cost effective and attractive alternative to conventional terrazzo flooring in hallways, restrooms and buffet areas. It's unaffected by repeated use of detergents or cleaning compounds. **Kennels** It is resistant to urine and we have a special slip-free finish that will not hurt animals paws. **Food Processing** it's clean, sanitary and withstands heavy steel wheel traffic, **Freezers** it withstands low temperatures, **Restaurant Kitchens** it provides a slip-resistant surface, even when wet. **Health Inspectors** love it because there are no joints or crevices to trap dirt or food particles. EVERLAST FLOOR® withstands sever exposures to grease, oil, water soaking, many acids, alkali, heavy traffic, sugar, animal fats, blood, salt and other corrosive materials.

FEATURES

- Non-porous and non-absorbent
- Chemical resistant
- Impact and shock resistant
- Excellent low temperature properties
- Unlimited life expectancy
- Low odor – no voc's
- No joints or seams for water penetration
- Anti-microbial – bacteria will not collect
- No delamination
- Available in many color combinations

PACKAGING

• Packaged in a 3-component kit; a box of aggregates, a gallon can of the mainresin and a quart can of curing agent. One kit covers approximately 25 sf of floor

PHYSICAL/CHEMICAL CHARACTERISTICS

PROPERTY	TYPICAL VALUES
SHELF LIFE	2 years (between 50°F and 85°F) (10°C and 29°C)
APPLICATION TEMP & HUMIDITY	55°F to 90°F (13°C to 30°C) @ less than 75% R.H.
MIXING RATIO	All components to be completely mixed together. Units are not to be split.
COVERAGE	Apx. 25 sf. Per unit
WORKING TIME	20-30 minutes @ 75°F (24°C)
APPLICATION METHOD	Mixed, poured and troweled
READY FOR TOP DRESSING	8 – 12 hours
READY FOR FOOT TRAFFIC	10-16 hours
READY FOR HEAVY TRAFFIC	1 week
ADHESION STRENGTH	>500 psi) w/ concrete failure (ASTM D-4541)
COMPRESSIVE STRENGTH	17,000 psi (ASTM D-579)
TENSILE STRENGTH	7,100 psi (ASTM D-307)
FLEXURAL STRENGTH	10,000 psi (ASTM D-580)
COEFFICIENT OF LINEAR EXPANSIO	2.5 x10-5 (ASTM D-696)
VOC	No VOC'S
SMOKE DENSIT	<3 (ASTM E-662)
IMPACT RESISTANCE	>24,000 psi (ASTM D-4226)
INDENTATION	0.8% (ASTM D-2794 - shall not exceed 1%)
ABRASION RESISTANCE	0.018gm (ASTM D-501)
FLAMMABILITY/EAT RESISTANCE	Self-Extinguishing (ASTM D-635)
HEAT RESISTANCE	158°F (ASTM D-2794)
WATER ABSORPTION	>0.2% (ASTM C-413)
WEIGHT	1.17 lbs/sf. @1/8" thickness
SLIP RESISTANCE	Wet leather Static 1.05 / Sliding 0.74 Wet rubber Static 1.10 / Sliding 0.72

Based upon a seven day cure at 75°F (24°C)

SURFACE PREPARATION

The substrate must be clean, dry and sound. Remove dust, laitance, grease, curing compounds, waxes, foreign particles and any previously applied potentially incompatible coatings by scarifying, chipping, wire brushing, acid etching, or pressure washing. If pressure washing or any other liquid method is used for prep, substrate should be fully rinsed, squeeze-dry mopped and allowed to completely dry. If the surface is not prepared properly, product adhesion will fail and warranties will be voided. Moisture vapor transmission reading must be 3 lbs. or less.

Concrete New concrete must cure for at least 28 days at 70°F (21°C), and have been free from water for at least 7 days. Older floors should be scarified and thoroughly cleaned. If badly cracked, crumbling, punky or deeply contaminated with oil or fat, a new concrete topping of proper thickness and strength should be installed. Swollen areas should be chipped out and any cracks, spalls, joints or other depressions filled with our underlayment.

Wood Floors Plywood floors should consist of 2 layers of at least 5/8" material with offsetting joints, and be screwed (nailing not acceptable) into 16" joists.

Vinyl Tile should be thoroughly cleaned to eliminate any wax buildup. Any loose tiles and adhesive must be removed and areas patched with our underlayment. Sheet flooring and adhesive must be completely removed.

Quarry / Ceramic Tile and grout must be thoroughly cleaned. Any loose tile must be removed and filled in with an approved underlayment. Glaze must be removed from the tile prior to installing Everlast Floor.

Steel Decks must be clean, free from oil, grease, rust and loose scale. The deck should then be wiped with denatured alcohol. Allow deck to dry.

FOR BEST RESULTS

- For Interior Use Only, UV Rays Cause Yellowing
- New Concrete Must Cure For at Least 30 Days @ 70°F (21°C).
- DO NOT thin EVERLAST FLOOR.
- DO NOT Use when Humidity Exceeds 75% Indoors.
- Temperatures should be Between 55°F and 90°F.
- Apply Top Dressing Within 24 Hours.
- Discard any Material Subjected to Freezing.
- DO NOT Apply to Structurally Unsound Surfaces.
- DO NOT Allow Mixed Material to sit in the Bucket.
- DO NOT Mix Material before you are Ready to Apply.
- Pour Entire Contents of Bucket out on the Floor at Once.

MIXING:

Avoid mixing and application of this product if the floor temperature is below 55°F or above 90°F. Also avoid application if the humidity is higher than 75% R.H. The temperature of the floor, materials and air in the area of the installation all play a role in how the product will apply and cure. To begin, you will need a clean 5-gallon pail and a ½ horsepower variable speed mixer. Open the gallon can and the quart can and empty contents into the mixing pail, making sure all

resin is removed from the cans to ensure consistency and performance. Blend resins for a minimum of 1 and ½ minutes. Add aggregates to the resin mixture and blend thoroughly.

POT LIFE

At 75°F (24°C) and 50% relative humidity, EVERLAST FLOOR has a useful working time or pot life of approximately 20-30 minutes. Using beyond this time will result in variable results and therefore any mixed product beyond the pot life should be discarded. Apply all material to the floor as quickly as possible to increase working time.

APPLICATION

For cove base, place mixed product on the floor along the wall. Use a bull-nose gauge trowel and place the material tightly against the wall at the required height. If necessary, tape the wall first to create a straight stopping point. Remove the tape immediately after troweling base. A large dinner spoon will form a nice cove finish.

For Floor, after mixing, pour product onto floor at once to increase working time. Material left in bucket has less working time. Using a Marshalltown finish trowel place the product with medium pressure, start at the wall and pull material toward you to flatten the product and finish material into its designed even thickness. Repeat until the product is constantly uniform. After the product has been placed, lighten up and hold the trowel at an angle and comb over the top of the material lightly. This will flatten any stones that may be high as well as supply more resin to the surface to seal off the system properly. The passes with the trowel till pull the resin to the top much the same way water will do in a cement application.

CLEAN UP

Application equipment should be cleaned using denatured alcohol immediately after use.

DISPOSAL

Empty containers may contain product residue. Do not cut, puncture or weld near these containers. Label warnings must be observed until containers have been commercially cleaned or reconditioned. Containers to be thrown out must be disposed in accordance with federal, state and local regulations. Use only licensed hazardous waste disposal companies.

CUSTOMER NOTE

One should not attempt to install Everlast Floor without first getting proper training from Everlast Epoxy Systems. An installation support webpage complete with a 28 minute training video and supporting documents are available to Everlast Floor customers. Do not attempt an installation prior to reviewing it. For more information contact your local Everlast Epoxy System's representative or the corporate office at 386-719-9979.

For more information about Everlast Epoxy Flooring visit www.everlastepoxy.com

WARRANTY STATEMENT

Information about EVERLAST EPOXY products is given to the best of our knowledge, based on tests and experience. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you will make your own tests to determine the suitability of the product for your particular purpose. As products are often applied or used under conditions beyond our control, EVERLAST EPOXY cannot guarantee anything but the quality of its products. EVERLAST EPOXY warrants that its products meet the specifications set forth by EVERLAST EPOXY, but we reserve the right to change any given specification without prior notice. EVERLAST EPOXY DISCLAIMS ALL WARRANTIES RELATING TO THE PRODUCTS AND THEIR APPLICATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Receipt of an EVERLAST EPOXY product constitutes acceptance of the terms of this limited warranty and the terms and conditions set out in our invoice, contrary provisions of buyer's purchase documents notwithstanding. Upon receipt of merchandise, purchaser has 30 days to notify EVERLAST EPOXY in writing that materials are defective. In the event EVERLAST EPOXY finds that the product delivered is off specification, EVERLAST EPOXY will, at its sole discretion, either replace the product or refund the purchase price thereof, and EVERLAST EPOXY's choice of one of these remedies is the buyer's sole remedy. In no event shall the liability of EVERLAST EPOXY exceed the purchase price of shipped merchandise. Claims must be in writing. Claims after 30 days are void. EVERLAST EPOXY will, under no circumstances, be liable for special, incidental or consequential damages. This warranty supersedes all other guarantees, whether oral or written, and whether expressed, implied or statutory. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Certain products may contain chemicals that may cause serious physical injury. Before using, please read the Material Safety Data Sheet and follow all precautions to prevent bodily harm.

Everlast Epoxy Systems Inc

637 NW State Road 47

Lake City, FL 32025 USA.

Phone (386) 719-9979

Fax (386) 719-6982

Email info@everlastepoxy.com
www.EverlastEpoxySystems.com