

EEFL203

Everlast® Stay-Clean Sealant UVR

DESCRIPTION

Everlast® Stay-Clean Sealant UVR is a UV Resistant two component 100% solids epoxy clear coating designed for applications where a stain and chemical resistant floor is needed. Its outstanding broad spectrum chemical resistance provides protection in aggressive environments. Everlast® Stay-Clean Sealant UVR meets all of the USDA guidelines for use in federally inspected facilities.

RECOMMENDED USES

Recommended for a finish coat over Everlast Industrial UVR, Everlast Integral Cove and Wall, Everlast Industrial UVR Flex and/or Everlast Industrial FS.

LIMITATIONS

Gloss may be affected by environmental conditions such as high humidity or chemical exposure. This product is not UV color stable and will discolor when exposed to UV light or some other forms of lighting such as sodium vapor lights. However, this product should not be topcoated without a thorough field test to evaluate coating compatibility and adhesion characteristics. Substrate temperature must be 5°F (3°C) above dew point. Slab on grade requires a moisture vapor barrier. Improper mixing may result in product failure. Physical properties are typical values and not specifications. See reverse side for limitations of our liability and warranty.

CURE SCHEDULE (70°)

Tack free (dry to touch)	6-8 hours
Recoat	7-9 hours
Light foot traffic	8-10 hours
Full cure (heavy traffic)	7 days

PHYSICAL CHARACTERISTICS

PROPERTY	TYPICAL VALUES
SOLIDS BY WEIGHT	100% (+/- 1%)
SOLIDS BY VOLUME	100% (+/- 1%)
UV Irradiation (UV Resistance test)	35 δE @ 1000 hours ASTM G154
RECOMMENDED FILM THICKNESS	5-10 mils
COVERAGE PER GALLON	300 square feet per gallon @ 5 mils
MIX RATIO	2 parts (2 gallons) part A to 1 part (1 gallon) part B (by volume)
SHELF LIFE	1 year in unopened containers
FINISH CHARACTERISTICS	Gloss 60° Gloss Meter @ 73F, 50% RH 85 millage units
ABRASION RESISTANCE	Weight loss after 500 cycles/2 Kg wheel (mg) = 42 mg loss
ADHESION At 4 h, 23 °C, 50% RH	on dry concrete 951 psi ASTM D7234 Intercoat adhesion 5A ASTM D3359
VISCOSITY	210 cPs
FLEXURAL STRENGTH	94 MPa
TENSILE STRENGTH	9670 psi
HARDNESS	Shore D= 80/75
APPLICATION TEMPERATURE	50-90° F with relative humidity below 85% for best results.

CUSTOMER NOTE

One should not attempt to install an Everlast® Industrial Floor without first reviewing the how-to instructions available at: <https://www.everlastepoxy.com/how-to-install-epoxy-floors>

For more information about Everlast Epoxy Flooring visit www.everlastepoxy.com

WARRANTY STATEMENT

Information about EVERLAST EPOXY products is given to the best of our knowledge, based on tests and experience. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you will make your own test to determine the suitability of the product for your particular purpose. As products are often applied or used under conditions beyond our control, EVERLAST EPOXY cannot guarantee anything but the quality of its products. EVERLAST EPOXY warrants that its products meet the specifications set forth by EVERLAST EPOXY, but we reserve the right to change any given specification without prior notice. EVERLAST EPOXY DISCLAIMS ALL WARRANTIES RELATING TO THE PRODUCTS AND THEIR APPLICATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Receipt of an EVERLAST EPOXY product constitutes acceptance of our "Terms of Sale" published at <https://everlastepoxy.com/terms-of-sale>, contrary provisions of an EVERLAST EPOXY salesperson or the buyer's purchase documents notwithstanding. Upon receipt of merchandise, purchaser has 30 days to notify EVERLAST EPOXY in writing that materials are defective. In the event EVERLAST EPOXY finds that the product delivered is off specification, EVERLAST EPOXY will, at its sole discretion, either replace the product or refund the purchase price thereof, and EVERLAST EPOXY's choice of one of these remedies is the buyer's sole remedy. In no event shall the liability of EVERLAST EPOXY exceed the purchase price of shipped merchandise. Claims must be in writing. Claims after 30 days are void. EVERLAST EPOXY will, under no circumstance, be liable for special, incidental or consequential damages. Our "Terms of Sale", published at <https://www.everlastepoxy.com/terms-of-sale>, supersedes all other guarantees, whether oral or written, and whether expressed, implied or statutory. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Certain products may contain chemicals that may cause serious physical injury. Before using,, please read the Material Safety Data Sheet and follow all precautions to prevent bodily harm.

CHEMICAL RESISTANCE

REAGENT	TYPICAL VALUES
Acetic Acid, 10%	C
Acetone	D
Acid Dichromate	B
Activated Carbon (sample immersed in dry powder)	E
Aluminum Hydroxide	C
Aluminum Hydroxide, 28%	D
Amyl Acetate	C
Benzene	C
Butyl Alcohol	B
Carbon Tetrachloride	C
Chloroform	A
Chromic Acid, 60%	B
Coffee	D
Cola	E
Cresol	B
Detergent, Industrial	E
Dichloro Acetic Acid	A
Dimethylformamide	A
Dioxane	A
Distilled Water	E
Ethanol, 50%	E
Ethyl Acetate	A
Ethyl Alcohol	B
Ethyl Ether	B
Ferric Chloride	C
Fluorsilic Acid	C
Formaldehyde, 37%	C
Formic Acid, 90%	A
Furfural	B
Gasoline	C
Household Cleaner (Amonia)	C
Household Cleaner (Pinesol)	E
Hydraulic Fluid	E
Hydrochloric Acid, 10%	D
Hydrochloric Acid, 20%	C
Hydrochloric Acid, 37%	C
Hydrochloric Acid, 40%	B
Hydroflouric Acid, 48%	B
Hydrogen Peroxide, 28%	C
Hydrogen Peroxide, 3%	C
Iodine, Tincture of	C

CHEMICAL RESISTANCE

REAGENT	TYPICAL VALUES
Isopropyl	E
Kerosene	C
Lactic Acid, 10%	D
Methyl Alcohol	A
Methyl Ethyl Ketone	C
Methylene Chloride	A
Mineral Oil	E
Mineral Spirits	E
Mono Chlorobenzene	A
Motor Oil	E
Naphtahlene (Sample was placed in a container filled with Mothballs)	E
Nitric Acid, 20%	D
Nitric Acid, 30%	C
Nitric Acid, 70%	A
Phenol, 90%	B
Phosphoric Acid, 10%	B
Phosphoric Acid, 80%	A
Phosphoric Acid, 85%	E
Potassium Hydroxide, 10%	C
Potassium Hydroxide, 80%	C
Potassium Permanganate	C
Silver Nitrate, Saturated	C
Sodium Carbonate, 2%	E
Sodium Carbonate, 20%	E
Sodium Hydroxide, 10%	E
Sodium Hydroxide, 20%	E
Sodium Hydroxide, 40%	E
Sodium Hydroxide, 80%	D
Sodium Hydroxide, Flake	D
Sodium Sulfide, Saturated	C
Sulfuric Acid (77%), and Nitric Acid (70%), equal parts	C
Sulfuric Acid, 33%	D
Sulfuric Acid, 77%	C
Sulfuric Acid, 96%	C
Synthetic Sea Water (Aquarium Grade)	D
Toluene	D
Trichloroethylene	A
Xylene	E
Zinc Chloride, Saturated	E

RATING KEY

A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill D - 72 hour immersion, E - long term immersion.

NOTE

Extensive chemical resistance information is available through your sales representative.

